

# Specification Advice

For laying  
SureSet flexible resin bound aggregate surfacing



## Internal Floors (Solid)



### The typical depth of SureSet Permeable Paving surface:

A SureSet aggregate size of 3mm requires a 12mm depth layer of SureSet  
A SureSet aggregate size of 6mm requires a 16mm depth layer of SureSet  
A SureSet aggregate size of 10mm requires a 22mm depth layer of SureSet



Screed (laid by others)  
Minimum depth 25mm bonded screed  
Minimum depth 50mm unbounded screed



**Sub Floor slab**  
Minimum depth 100mm concrete e.g GEN1 Designated mix BS5238 S2 slump.



**Insulation**



**Damp Proof Course**  
**Sand blinding layer**  
**Consolidated Hardcore**



### Purpose

To provide an attractive, durable and seamless natural stone or gravel finish.

### Advantages

Rapidly applied and can be brought into service without delay.

### Notes

Screeds should be clean, dry and free from any contaminants. The use of a primer may be required.

# Specification Advice

QRSA7108  
Internal Floors

**SureSet**  
Permeable Paving

## Internal Floors



If you have any enquiries call our technical sales team on: +44 (0)1985 841180

*The details in this specification are intended only as a guide in specifying SureSet products, actual designs should be developed by the project designers taking into account the specific circumstances of the intended application. SureSet assumes no responsibility for improper reliance upon or misuse of the data herein. Product design and specification are subject to change without further notice.*

SureSet UK Ltd, 32 Deverill Road Trading Estate, Sutton Veny, Warminster, Wiltshire, BA12 7BZ  
+44 (0)1985 841180      mail@sureset.co.uk      www.sureset.co.uk